

# Hybrid Textile Polymer Composite Laminates For Structural Applications

Jyoti Rani (*Textile Engineering* ), Dept. of Engineering, Research Scholar, SunRise University , Alwar(Rajasthan)  
Dr. Praveen Kumar (*Textile Engineering*), Associate Professor (Dept. of Engineering), SunRise University , Alwar (Rajasthan)

## ABSTRACT

*Hybrid textile polymer composite laminates have emerged as promising materials for various structural applications due to their exceptional mechanical properties, lightweight nature, and design flexibility. This research paper provides a comprehensive review of the current state-of-the-art in hybrid textile polymer composite laminates, focusing on their manufacturing techniques, mechanical performance, and potential applications. Moreover, this paper identifies key challenges and presents future research directions to facilitate the widespread utilization of these materials in diverse structural applications.*

**Keywords:** *Hybrid textile polymer, Mechanical Properties.*

## INTRODUCTION

The introduction section of the research paper on hybrid textile polymer composite laminates for structural applications provides an overview of the background, motivation, definition of hybrid textile polymer composite laminates, and highlights the significance and scope of the research.

**Background and Motivation:** The aerospace, automotive, marine, and civil engineering industries are continuously seeking lightweight, high-strength materials for structural applications. Traditional materials like metals and alloys often exhibit limitations in terms of weight, corrosion resistance, and design flexibility. In this context, composite materials have gained significant attention due to their exceptional mechanical properties and versatility. Composite laminates, which consist of layers of fibers embedded in a polymer matrix, offer superior strength-to-weight ratios, corrosion resistance, and tailorabile mechanical properties. However, the use of single fiber types in composite laminates may not always meet the desired performance requirements for specific applications. To overcome this limitation and optimize the material properties, hybridization of different types of fibers has been explored.

### Definition of Hybrid Textile Polymer Composite Laminates:

Hybrid textile polymer composite laminates refer to composite materials that incorporate multiple types of fibers in a single laminate structure. These fibers can be sourced from natural, synthetic, or a combination of both materials. The fibers are typically woven or stitched together to form a textile reinforcement, which is then impregnated with a polymer matrix.

**Significance and Scope of the Research:** The research on hybrid textile polymer composite laminates holds significant importance in the field of structural materials due to several reasons:

**Enhanced Mechanical Performance:** Hybridization of different fibers allows for the optimization of mechanical properties, such as strength, stiffness, toughness, and impact resistance. The combination of fibers with complementary properties can lead to improved overall performance, surpassing the capabilities of single-fiber composites.

**Weight Reduction:** The utilization of lightweight fibers in hybrid laminates can lead to weight reduction in structural components. This property is of particular importance in industries like aerospace and automotive, where fuel efficiency and reduced emissions are key considerations.

**Design Flexibility:** Hybrid laminates offer the advantage of tailoring material properties based on specific application requirements. By strategically selecting and arranging different fiber types, designers and engineers can achieve a balance between strength, flexibility, and other functional requirements.

**Cost-effectiveness:** Hybridization of fibers can provide cost advantages by incorporating less expensive fiber types with high-performance fibers, thereby reducing material costs while maintaining desired mechanical properties.

**Sustainability:** The use of natural fibers in hybrid laminates offers an environmentally friendly alternative to traditional synthetic fibers. Natural fibers are renewable, biodegradable, and have lower carbon footprints compared to synthetic counterparts.

The scope of the research involves investigating various aspects of hybrid textile polymer composite laminates, including manufacturing techniques, mechanical performance evaluation, characterization methods, and potential applications. By addressing these aspects, the research aims to contribute to the understanding and advancement of hybrid textile polymer composite laminates, enabling their wider adoption in structural applications.

## **MANUFACTURING TECHNIQUES FOR HYBRID TEXTILE POLYMER COMPOSITE LAMINATES**

### **Resin Infusion Methods:**

**a. Vacuum Infusion:** Vacuum infusion is a manufacturing technique that involves the use of a vacuum bag to create a controlled environment for resin infusion. In this process, dry fiber preforms, such as woven or non-woven textiles, are placed in a mold. A vacuum bag is then sealed tightly around the mold, creating a vacuum-tight chamber. The resin is introduced into the mold either by gravity or by applying pressure, and the vacuum helps in drawing the resin through the fiber reinforcement. The resin impregnates the fibers, displacing any trapped air or excess resin. The vacuum is maintained until the resin cures, resulting in a fully consolidated hybrid laminate. Vacuum infusion offers good fiber impregnation, improved resin distribution, and is suitable for producing complex-shaped laminates.

**b. Resin Transfer Molding (RTM):** Resin transfer molding is a closed-mold process that involves injecting resin into a mold cavity containing dry fiber preforms. The preforms can be in the form of textiles, such as woven or stitched fabrics. The mold is closed, and the resin is injected under pressure into the mold cavity. The resin flows through the preform, impregnating the fibers. The pressure is maintained until the resin cures and the laminate solidifies. RTM allows precise control over resin flow, fiber volume fraction, and fiber orientation. It produces high-quality laminates with excellent mechanical properties, making it suitable for manufacturing hybrid textile polymer composite laminates.

### **Prepreg Manufacturing Techniques:**

**a. Hot Melt Impregnation:** Hot melt impregnation involves passing dry fiber reinforcements through a resin bath heated to a temperature where the resin becomes molten. The fibers are then coated with the molten resin, which impregnates the fiber matrix. Excess resin is removed by passing the impregnated fibers through a set of rollers, ensuring controlled resin content. The impregnated fibers, known as prepgres, are cooled and stored for subsequent use. Prepgres offer advantages such as controlled resin content, improved fiber impregnation, and ease of handling during layup.

**b. Solvent Dip:** Solvent dip method involves dipping dry fiber reinforcements into a solvent-based resin solution. The resin solution penetrates the fiber matrix, impregnating the fibers. The excess solvent is then evaporated, leaving behind resin-impregnated fibers. Solvent dip method allows for efficient resin impregnation and is suitable for impregnating complex-shaped and closely packed fibers.

**Resin Film Infusion:** Resin film infusion involves the use of pre-impregnated resin films, also known as prepreg films, for laminate production. These films consist of partially cured resin impregnated into the fiber reinforcement.

During the manufacturing process, dry fiber preforms are layered with alternating layers of resin film. The layup is then consolidated under heat and pressure, allowing the resin to flow and bond the layers together. The heat promotes resin flow and initiates the curing process, resulting in a fully consolidated laminate. Resin film infusion offers precise control over resin content and fiber volume fraction, ensuring uniform impregnation and high-quality laminates.

**Compression Molding:** Compression molding is a widely used manufacturing technique for hybrid textile polymer composite laminates. In this process, dry fiber preforms, such as woven fabrics or non-woven textiles, are placed between two heated mold halves. The mold is closed, and pressure is applied to compress the fibers and distribute the resin evenly. Heat and pressure are maintained until the resin cures, forming a consolidated laminate.

Compression molding allows for high-volume production, excellent fiber impregnation, and the ability to produce complex-shaped parts.

**Automated Fiber Placement and Tape Laying:** Automated fiber placement (AFP) and automated tape laying (ATL) are advanced manufacturing techniques that enable precise and automated placement of continuous fibers or narrow tapes onto molds or tooling.

**a. AFP:** Automated fiber placement involves the use of robotic systems to lay continuous fibers onto molds or tooling. The fibers are fed through a placement head, which moves along predefined paths to deposit the fibers accurately. AFP offers high fiber placement accuracy, repeatability, and the ability to control fiber angles, allowing the production of tailored hybrid laminates. It is suitable for complex-shaped components and allows for the incorporation of different fiber types in specific regions of the laminate.

**b. ATL:** Automated tape laying involves the placement of narrow tape-like fibers onto molds or tooling. The tapes are cut to the desired length and placed onto the mold using automated machinery. ATL provides flexibility in controlling fiber orientation and allows for the integration of multiple fiber types in a single laminate. It offers high-speed layup, precise fiber placement, and reduced material waste.

#### Hybridization Strategies:

**a. Interlayer Hybridization:** Interlayer hybridization involves the use of different fiber types in adjacent layers of the laminate. By alternating different fiber materials, the laminate can benefit from the specific properties offered by each fiber type. For example, a layer with high-strength carbon fibers can be combined with a layer of impact-resistant aramid fibers to achieve a balance between strength and toughness in the laminate.

**b. Intralayer Hybridization:** Intralayer hybridization refers to the incorporation of multiple fiber types within a single layer of the laminate. This can be achieved through techniques such as weaving or stitching different fibers together to form a hybrid textile reinforcement. Intralayer hybridization allows for tailored fiber architectures, enabling the optimization of specific mechanical properties within a single layer.

Both interlayer and intralayer hybridization strategies enable the design of hybrid textile polymer composite laminates with enhanced mechanical properties, such as improved strength, stiffness, toughness, and impact resistance. These strategies offer flexibility in tailoring the material properties to suit specific application requirements.

### MECHANICAL PERFORMANCE OF HYBRID TEXTILE POLYMER COMPOSITE LAMINATES

Hybrid textile polymer composite laminates offer a unique combination of mechanical properties derived from the integration of different fiber types within a single laminate. The mechanical performance of these laminates can be assessed through various testing methods to evaluate their suitability for structural applications. Here, we explain the key aspects of mechanical performance:

**Tensile, Compressive, and Flexural Properties:** *Tensile, compressive, and flexural properties are essential measures of a laminate's strength, stiffness, and deformation behavior.*

**Tensile Strength and Modulus:** Tensile testing involves applying an axial load to a specimen to assess its resistance to stretching or elongation. The tensile strength represents the maximum load the laminate can withstand before failure, while the tensile modulus indicates its stiffness or resistance to deformation under tension.

**Compressive Strength and Modulus:** Compressive testing applies an axial load to a specimen in a direction opposite to tension, evaluating the laminate's ability to withstand compressive forces. Compressive strength represents the maximum load it can bear before failure, while the compressive modulus indicates its resistance to compression.

**Flexural Strength and Modulus:** Flexural testing evaluates a laminate's resistance to bending. A three-point or four-point bending test is commonly conducted to measure the flexural strength and modulus, which indicate the laminate's ability to withstand bending forces without fracture.

**Impact and Fracture Toughness:** *Impact and fracture toughness characterize a laminate's ability to absorb energy and resist crack propagation.*

**Impact Resistance:** Impact testing subjects a specimen to a sudden load or impact to measure its ability to absorb energy without failure. It assesses the laminate's resistance to dynamic loading and provides insights into its performance under impact events.

**Fracture Toughness:** Fracture toughness measures a laminate's resistance to crack propagation and is determined through testing methods such as the Charpy or Izod impact test, or by conducting fracture mechanics-based tests. Fracture toughness evaluation is crucial for assessing the laminate's ability to withstand crack initiation and propagation.

**Fatigue and Durability:** Fatigue testing assesses a laminate's resistance to cyclic loading, simulating repeated stress cycles over time. This testing is essential for applications subjected to cyclic loading conditions, such as aerospace or wind turbine components. Fatigue testing helps determine the laminate's endurance limit, fatigue life, and degradation behavior under cyclic loading.

**Thermal Properties:** *Thermal properties characterize a laminate's behavior under varying temperature conditions.*

**Coefficient of Thermal Expansion (CTE):** CTE measures how the laminate's dimensions change with temperature variations. Understanding the CTE is important for applications where dimensional stability is critical, as high CTE values can result in dimensional variations and stress accumulation.

**Thermal Conductivity:** Thermal conductivity determines a laminate's ability to conduct heat. It affects heat dissipation, thermal management, and temperature distribution within the structure.

**Environmental Resistance:** *Environmental resistance testing assesses the laminate's performance under specific environmental conditions.*

**Moisture Absorption:** Moisture absorption testing measures the amount of water absorbed by the laminate over time. It helps evaluate the laminate's dimensional stability, strength retention, and resistance to moisture-induced degradation.

**Chemical Resistance:** Chemical resistance testing evaluates the laminate's performance when exposed to specific chemicals, including acids, bases, solvents, and fuels. It assesses the laminate's resistance to chemical degradation, swelling, or loss of mechanical properties.

**UV Resistance:** UV resistance testing examines the laminate's ability to withstand prolonged exposure to ultraviolet (UV) radiation. It helps evaluate the laminate's resistance to degradation, color fading, and loss of mechanical properties due to UV exposure.

## **CHARACTERIZATION TECHNIQUES FOR HYBRID TEXTILE POLYMER COMPOSITE LAMINATES**

*Characterization techniques for hybrid textile polymer composite laminates typically include the following methods:*

### **Non-destructive testing Methods:**

**Ultrasonic Testing:** This technique uses high-frequency sound waves to detect internal defects, delaminations, and voids within the composite laminate. Ultrasonic waves are transmitted through the material, and the reflected waves are analyzed to identify any anomalies.

**Thermography:** Infrared thermography involves using thermal imaging cameras to detect variations in temperature distribution on the surface of the composite laminate. This method can identify defects, such as delaminations, disbonds, and voids, by analyzing thermal patterns.

### **Microscopy and imaging techniques:**

**Optical Microscopy:** It involves using visible light to examine the microstructure and morphology of the hybrid textile polymer composite. This technique can provide information about fiber orientation, fiber-matrix interface, and overall laminate quality.

**Scanning Electron Microscopy (SEM):** SEM provides high-resolution images of the composite surface and cross-section. It is useful for analyzing fiber-matrix adhesion, interfacial properties, and identifying failure mechanisms at a microstructural level.

**X-ray Microscopy:** X-ray imaging techniques, such as microcomputed tomography (micro-CT), can provide 3D visualization and analysis of the internal structure and defects of the composite laminate.

#### **Mechanical testing:**

**Tensile Testing:** Tensile tests measure the strength, stiffness, and elongation properties of the composite laminate in tension. This test helps determine the material's mechanical behavior, including ultimate tensile strength, modulus of elasticity, and failure mode.

**Flexural Testing:** Flexural tests evaluate the bending properties and stiffness of the composite laminate. It measures properties such as flexural strength, flexural modulus, and interlaminar shear strength.

**Impact Testing:** Impact tests assess the composite laminate's resistance to sudden loading and its ability to absorb energy during impact events. This test helps determine the material's impact strength, toughness, and damage tolerance.

#### **Thermal Analysis:**

**Differential Scanning Calorimetry (DSC):** DSC measures the heat flow associated with phase transitions, curing, and thermal stability of the composite laminate. It can determine properties such as glass transition temperature, curing kinetics, and degree of cure.

**Thermogravimetric Analysis (TGA):** TGA measures weight changes in the composite laminate as a function of temperature. It helps determine the thermal stability, decomposition temperature, and the presence of fillers or additives in the material.

**Dynamic Mechanical Analysis (DMA):** DMA measures the viscoelastic properties of the composite laminate as a function of temperature, frequency, and applied stress/strain. It provides information on storage modulus, loss modulus, damping properties, and viscoelastic transitions such as glass transition.

### **APPLICATIONS OF HYBRID TEXTILE POLYMER COMPOSITE LAMINATES**

#### **Spaceflight and Air Travel:**

- Hybrid composites are ideal for aeronautical uses because of their light weight and excellent strength-to-weight ratio. They help planes fly more efficiently and carry more cargo by minimising excess weight.
- Aircraft structural components made from these composites include wings, fuselage panels, interior pieces, and more. Their mechanical characteristics, durability, and fatigue resistance are unparalleled.

#### **The Automobile Business:**

- Automobiles benefit from greater fuel efficiency and less emissions thanks to the use of hybrid textile polymer composites, which allow for significant weight savings.
- High energy absorption characteristics of these materials improve passenger safety in the case of a collision.
- Reducing NVH (Noise, Vibration, and Harshness): Hybrid composites can help make a car quieter and more peaceful inside.

#### **Wind Power:**

- Wind turbine rotor blades are typically made from hybrid textile polymer composites. They provide effective energy conversion thanks to their high strength, stiffness, and fatigue resistance.
- These composites have the potential for low-cost and scalable production processes, making them well-suited for the large-scale manufacture of wind turbine parts.

#### **Naval and Marine Uses:**

- Hybrid composites are utilised for the hulls, decks, and other structural components of boats and ships. Their high strength, resistance to corrosion, and low weight enhance the performance of the vessel and decrease its fuel consumption.
- These composites are used in offshore platforms, undersea constructions, and marine renewable energy devices because of their long lifespan, tolerance to severe environments, and high mechanical strength.

#### **Construction Engineering and Public Works:**

- Hybrid textile polymer composites are used in the building of bridges, footbridges, and other types of infrastructure. They are extremely sturdy, long-lasting, and proof against the elements.
- Existing constructions, such as concrete columns, beams, and slabs, can be reinforced or rehabilitated with the help of these composites. They improve the infrastructure's durability and reliability

## CHALLENGES AND LIMITATIONS

### Cost-Effectiveness:

- Materials: Advanced materials used in emerging technologies can be expensive, impacting the overall cost-effectiveness of the manufacturing processes.
- Research and Development: Extensive R&D efforts are often required to develop and optimize new technologies, which can be costly.
- Economy of Scale: Achieving cost-effectiveness can be challenging without large-scale production, as the initial setup costs and low production volumes may result in higher per-unit costs.

### Scalability of Manufacturing Processes:

- Production Capacity: Scaling up manufacturing processes for emerging technologies can be complex, requiring adjustments and improvements to increase production capacity.
- Automation and Robotics: Implementing automated manufacturing systems suitable for emerging technologies may require significant investment and expertise.
- Supply Chain: Expanding manufacturing capacity often involves establishing a robust supply chain to ensure a steady flow of raw materials and components.

### Structural Design and Optimization:

- Design Complexity: Emerging technologies often involve intricate and complex designs that require specialized knowledge and tools for optimization.
- Simulation and Modeling: Developing accurate simulation and modeling techniques for structural analysis and optimization can be challenging, particularly for novel materials and designs.
- Iterative Processes: Iterative design and optimization cycles may be necessary to refine and improve structural performance, which can increase development time and cost.

### Environmental Impact and Sustainability:

- Resource Consumption: Emerging technologies may require significant amounts of raw materials, including rare or precious elements, which can strain natural resources.
- Energy Consumption: Manufacturing and operating emerging technologies can have high energy demands, leading to increased carbon emissions and environmental impact.
- Waste Management: Proper disposal or recycling of materials used in emerging technologies can pose challenges, especially when dealing with hazardous substances or complex composites.

### Standardization and Certification:

- Lack of Standards: Emerging technologies often lack established industry standards, making it difficult to ensure interoperability, safety, and quality control.
- Regulatory Compliance: Obtaining necessary certifications and meeting regulatory requirements can be time-consuming and costly, particularly if specific standards are not in place.
- Testing and Validation: Developing appropriate testing methodologies and protocols for emerging technologies can be challenging, as they may require innovative approaches to evaluate performance, safety, and reliability.

## FUTURE PERSPECTIVES AND RESEARCH DIRECTIONS

In the future, research in various areas will pave the way for groundbreaking developments in emerging technologies. Novel reinforcement materials and architectures hold the promise of enhancing structural performance and unlocking unprecedented capabilities. Advanced manufacturing techniques, such as 3D printing and automated processes, will revolutionize production, enabling cost-effective and scalable manufacturing of complex components. Multifunctional hybrid composites will blur traditional material boundaries, leading to

lightweight, yet highly versatile materials with multiple functionalities. Modeling and simulation approaches will play a pivotal role in streamlining the design and optimization processes, ensuring efficient and accurate development of emerging technologies. Recycling and sustainability initiatives will be imperative, addressing environmental concerns and establishing closed-loop systems to reduce waste and promote a more sustainable future. Collectively, these research directions will usher in a new era of innovation and transformative technologies, revolutionizing industries and positively impacting society at large.

## CONCLUSION

**Summary of Key Findings:** The key findings in the field of hybrid textile polymer composite laminates highlight their immense potential for various applications. Hybrid laminates combine different textile reinforcements, such as carbon fibers, glass fibers, or aramid fibers, with polymer matrices to create lightweight and high-strength materials. These laminates exhibit improved mechanical properties, including tensile strength, stiffness, and impact resistance, compared to traditional composites. Additionally, they offer enhanced design flexibility, as different fiber orientations and combinations can be tailored for specific load requirements. The integration of textiles into composite laminates also provides benefits such as improved damage tolerance, energy absorption, and fatigue resistance. Overall, hybrid textile polymer composite laminates offer a promising solution for lightweight and high-performance materials in sectors like aerospace, automotive, sports equipment, and infrastructure.

**Potential Impact of Hybrid Textile Polymer Composite Laminates:** The potential impact of hybrid textile polymer composite laminates is significant across various industries. In the aerospace sector, these laminates can contribute to weight reduction in aircraft structures, resulting in improved fuel efficiency and reduced emissions. Their high strength-to-weight ratio makes them suitable for critical components such as fuselage sections, wings, and engine parts. In the automotive industry, hybrid laminates can enable the production of lightweight vehicles, leading to enhanced energy efficiency and reduced carbon footprint. Moreover, their excellent impact resistance makes them valuable for crash safety applications. In sports equipment, the use of hybrid laminates can enhance performance by providing superior strength, durability, and impact resistance in products like tennis rackets, hockey sticks, and bicycle frames. The construction industry can benefit from the lightweight nature of these laminates, facilitating easier transportation, installation, and reducing structural loads. The potential impact of hybrid textile polymer composite laminates extends to various other fields where lightweight and high-performance materials are in demand.

**Final Remarks and Future Prospects:** Hybrid textile polymer composite laminates represent a promising area of research and development with a wide range of potential applications. As research continues, there are several key areas that warrant attention for future prospects. First, further advancements in manufacturing techniques are needed to optimize the fabrication of hybrid laminates, ensuring cost-effectiveness and scalability. This includes exploring automated processes, additive manufacturing technologies, and improved material deposition methods. Additionally, the development of predictive modeling and simulation approaches will aid in the design optimization and structural analysis of hybrid laminates, reducing time and costs associated with physical prototyping. Recycling and sustainability initiatives should also be prioritized to address the end-of-life management of these materials, promoting circular economy principles and minimizing environmental impact. Collaborations between academia, industry, and regulatory bodies are crucial to drive innovation, establish industry standards, and facilitate the widespread adoption of hybrid textile polymer composite laminates. With continued research and technological advancements, these laminates have the potential to revolutionize multiple industries, offering lightweight, high-strength, and environmentally sustainable solutions for diverse applications.

## REFERENCES

1. Das, S., & Chakraborty, D. (2019). Mechanical and dynamic mechanical properties of banana/jute/glass hybrid fiber-reinforced polymer composites. *Polymer Composites*, 40(12), 4651-4660.
2. Mohanty, S., Nayak, S. K., & Verma, S. K. (2018). Effect of hybridization on the mechanical properties of natural fiber-reinforced polymer composites. *Journal of Composite Materials*, 52(9), 1249-1260.
3. Vigneshwaran, N., & Arunachalam, R. M. (2016). Mechanical and dynamic mechanical properties of hybrid jute-sisal-glass fiber reinforced polymer composites. *Journal of Reinforced Plastics and Composites*, 35(10), 785-793.
4. Bhat, A. H., & Sain, M. M. (2014). Hybrid composites made from natural fiber (hemp, jute) reinforced polypropylene and jute fabric reinforced epoxy. *Journal of Reinforced Plastics and Composites*, 33(12), 1153-1166.
5. Kumar, S., Singh, V., & Dwivedi, A. K. (2013). Mechanical properties of randomly oriented short banana/sisal hybrid fiber-reinforced epoxy composites. *Journal of Reinforced Plastics and Composites*, 32(11), 811-823.
6. Vijay, R., & Kumar, S. (2012). Mechanical behavior of jute-coir hybrid fiber-reinforced epoxy composites. *Journal of Reinforced Plastics and Composites*, 31(15), 1063-1075.
7. Chakraborty, D., & Das, S. (2012). Mechanical properties of banana/jute fiber-reinforced hybrid composites. *Journal of Reinforced Plastics and Composites*, 31(4), 247-259.
8. Jose, S., Thomas, S., & Koshy, P. (2011). Dynamic mechanical analysis of banana/sisal hybrid fiber-reinforced polyester composites. *Journal of Reinforced Plastics and Composites*, 30(7), 555-564.
9. Nayak, S. K., & Mohanty, A. K. (2011). Mechanical properties of jute/banana hybrid composites: Role of stacking sequence and fiber orientation. *Journal of Reinforced Plastics and Composites*, 30(2), 157-166.
10. Manikandan, V., & Senthilkumar, V. (2010). Evaluation of mechanical properties of randomly oriented short banana/jute hybrid fiber-reinforced polyester composites. *Journal of Reinforced Plastics and Composites*, 29(24), 3699-3709.
11. Kanny, K., & Pitchaimani, J. (2010). Tensile and impact properties of hybrid composites of jute and kenaf fabrics with glass fiber reinforced composites. *Journal of Reinforced Plastics and Composites*, 29(20), 3012-3023.
12. Khanam, P. N., Kumar, G. S., & Naik, N. K. (2010). Mechanical behavior of short jute-sisal reinforced hybrid composites. *Journal of Reinforced Plastics and Composites*, 29(4), 555-565.
13. Rahman, M., & Pandey, K. M. (2009). Characterization of jute and mesta fiber reinforced epoxy composites. *Journal of Reinforced Plastics and Composites*, 28(11), 1377-1387.